

# **KIBABII UNIVERSITY**

**UNIVERSITY EXAMINATIONS  
2021/2022 ACADEMIC YEAR**

**FOURTH YEAR SECOND SEMESTER  
SUPPLEMENTARY EXAMINATIONS**

**FOR THE DEGREE OF B.SC (PHYSICS)**

**COURSE CODE: SPM 422**

**COURSE TITLE: THE COMPOSITES**

**DURATION: 2HRS**

**DATE: 23/11/2022**

**TIME: 11:00AM-1:00PM**

---

## **INSTRUCTIONS TO CANDIDATES**

- Answer question ONE (compulsory) and any TWO of the remaining questions.
- Attempted questions must be indicated on front cover of answer booklet.
- Every question should be started on new page and question indicated respectively.

KIBU observes ZERO tolerance to examination cheating

### QUESTION ONE (30MKS)

- a. Its important for the creation of ceramic matrix composites, state the major reason import  
(2mks)
- b. Calculate the elastic modulus of the Glass Fiber-Reinforced Composite-Transverse Direction composite assuming that the stress is applied perpendicular to the direction of fiber alignment.  
(4mks)
- c. What are the differences in strengthening mechanisms for large particle and dispersion-strengthened particle reinforced composites?  
(4mks)
- d. Cite one desirable characteristic and one less desirable characteristic for each of
  - a. Discontinuous-oriented fiber-reinforced composites. (2mks)
  - b. Discontinuous-randomly oriented fiber-reinforced composites. (2mks)
- e. Distinguish between pure materials and composite materials, hence State the reason why composites are preferred over pure materials.  
(3mks)
- f. Name and briefly discuss two sub-classification of structural composites. (4mks)
- g. For a fiber-reinforced composite, the efficiency of reinforcement is dependent on fiber length  $l$  according to  $\eta = \frac{l-2x}{l}$ , where  $x$  represents the length of the fiber at each end that does not contribute to the load transfer. Make a plot of  $\eta$  versus  $l$  to  $l = 50$  mm (2.0 in.) assuming that  $x = 1.25$  mm (0.05 in.).  
(5mks)
- h. Name the two main divisions of composite materials citing the distinguishing features of each.  
(4mks)

### QUESTION TWO (20MKS)

- a. A continuous and aligned glass fiber-reinforced composite consists of 40 vol% of glass fibers having a modulus of elasticity of 69 GPa ( $10 \times 10^6$  psi) and 60 vol% of a polyester resin that, when hardened, displays a modulus of 3.4 GPa ( $0.5 \times 10^6$  psi).
  - (a) Compute the modulus of elasticity of this composite in the longitudinal direction.  
(4mks)
  - (b) If the cross-sectional area is 250 mm<sup>2</sup> (0.4 in.<sup>2</sup>) and a stress of 50 MPa (7250 psi) is applied in this longitudinal direction, compute the magnitude of the load carried by each of the fiber and matrix phases.  
(4mks)
  - (c) Determine the strain that is sustained by each phase when the stress in part (b) is applied.  
(4mks)

- b. In the table below are listed four hypothetical aligned fiber-reinforced composites (labeled A through D), along with their characteristics.

Composite	Fiber type	Vol fraction Fibers	Fiber strength (MPa)	Aver fiber length (mm)	Critical length (mm)
A	Glass	0.2	$3.5 \times 10^3$	8	0.70
B	Glass	0.35	$3.5 \times 10^3$	12	0.75
C	Carbon	0.40	$5.5 \times 10^3$	8	0.40
D	Carbon	0.30	$5.5 \times 10^3$	8	0.50

On the basis of these data, rank the four composites from highest to lowest strength in the longitudinal direction, and then justify your ranking.

### QUESTION THREE

- With suitable sketches, explain the filament winding method of producing a polymer matrix composite. (8mks)
- Derive an expression for the modulus of elasticity for a continuous and aligned fibrous composite loaded in the direction of alignment. (12mks)

### QUESTION FOUR (20 MKS)

- Carbon is a high-performance fiber material that is the most commonly used reinforcement in advanced polymer-matrix composites. Discuss any five reasons why Carbon Fiber-Reinforced Polymer (CFRP) Composites is commonly used. (10mks).
- Show that for longitudinal loading, the ratio of the load carried by the fibers to that carried by the matrix is given by  $\frac{F_f}{F_m} = \frac{E_f V_f}{E_m V_m}$  where the initials have their usual meaning. (10mks)

### QUESTION FIVE (20MKS)

- The mechanical properties of cobalt may be improved by incorporating fine particles of tungsten carbide. Given that the moduli of elasticity of these materials are, respectively, 200 GPa (psi) and 700 GPa (psi), plot modulus of elasticity versus the volume percent of tungsten carbide in cobalt from 0 to 100 vol%, using both upper- and lower bound expressions. (8mks)
- A continuous and aligned fibrous reinforced composite having a cross-sectional area of  $970 \text{ mm}^2$  ( $1.5 \text{ in.}^2$ ) is subjected to an external tensile load. If the stresses sustained by the fiber and matrix phases are 215 MPa (31,300 psi) and 5.38 MPa (780 psi), respectively, the force sustained by the fiber phase is 76,800 N ( $17,265 \text{ lb}_f$ ), and the total longitudinal composite strain is  $1.56 \times 10^{-3}$ . Determine
  - The force sustained by the matrix phase. (4mks)

- (b) The modulus of elasticity of the composite material in the longitudinal direction (4mks)
- (c) The moduli of elasticity for fiber and matrix phases. (4mks)